

10005465 AQUAMID 66G15 NERO

Emission date 23/08/2024

AQUAMID 66G15 NERO is a black color PA66 grade, filled with 15% glass fiber content and suitable for injection moulding applications.

Ed./Rev. 2.0

DESCRIPTORS		
Symbol	ISO 1043	PA66-GF15
Designation	ISO 16396-1	-PA 66,GF15,MGCR,S14-060N
Part Marking	ISO 16396-1	>PA 66-GF15<

PROPERTIES	STANDARD	CONDITION	UNIT	VALUES	
PHYSICAL PROPERTIES				d.a.m.*	cond.*
Density	ISO 1183		g/cm3	1,26	-
Melt Volume Rate (MVR)	ISO 1133	275°C x 2,16 kg	cm3/10'	25	-
Moisture Absorption	ISO 62	23°C, 1000h	%	-	-
Moisture Content	Int. Method		%	max 0,2	-
Mold Shrinkage (Longitudinal)	ISO 2577	72h,23°C,50% RH	%	-	-
Mold Shrinkage (Transversal)	ISO 2577	72h,23°C,50% RH	%	-	-
MECHANICAL PROPERTIES				d.a.m.*	cond.*
Tensile Modulus	ISO 527	1 mm/min	MPa	5800	-
Tensile Strength	ISO 527	50 mm/min	MPa	130	-
Tensile Stress, Yield	ISO 527	50 mm/min	MPa	-	-
Tensile Strain, Yield	ISO 527	50 mm/min	%	-	-
Tensile Stress, Break	ISO 527	50 mm/min	MPa	130	-
Tensile Strain, Break	ISO 527	50 mm/min	%	4,0	-
Flexural Modulus	ISO 178	2 mm/min	MPa	-	-
Flexural Stress, Break/max	ISO 178	2 mm/min	MPa	-	-
Flexural Strain, Break/max	ISO 178	2 mm/min	%	-	-
IMPACT PROPERTIES				d.a.m.*	cond.*
Charpy, notched	ISO 179/1eA	+23°C	kJ/m2	-	-
Charpy, unnotched	ISO 179/1eU	+23°C	kJ/m2	-	-
Charpy, notched	ISO 179/1eA	-30°C	kJ/m2	-	-
Charpy, unnotched	ISO 179/1eU	-30°C	kJ/m2	-	-
Izod, notched	ISO 180/1A	+23°C	kJ/m2	4,0	-
Izod, unnotched	ISO 180/1U	+23°C	kJ/m2	30	-
Izod, notched	ISO 180/1A	-30°C	kJ/m2	-	-
Izod, unnotched	ISO 180/1U	-30°C	kJ/m2	-	-

GENERAL DISCLAIMER


The information provided in this document correspond to our technical knowledge at the date of its publication. This information may be subject to revision at our discretion. Aquafil cannot anticipate all conditions under which this information and/or products of other manufactures in combination with our products may be used. Aquafil accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Aquafil sells the product without warranties. Buyers and users assume all responsibilities and liability for loss or damage arising from handling and use of our product, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

10005465 AQUAMID 66G15 NERO

Emission date 23/08/2024
Ed./Rev. 2.0

AQUAMID 66G15 NERO is a black color PA66 grade, filled with 15% glass fiber content and suitable for injection moulding applications.

PROPERTIES	STANDARD	CONDITION	UNIT	VALUES	
THERMAL PROPERTIES				d.a.m.*	cond.*
Crystallization Temperature	ISO 11357	20°C/min, 0-280°C	°C	-	-
Melting Temperature	ISO 11357	20°C/min, 0-280°C	°C	260	-
HDT-B	ISO 75	0,45 MPa	°C	-	-
HDT-A	ISO 75	1,80 MPa	°C	-	-
VICAT	ISO 306	50°C/h - 50 N	°C	-	-
RTI, 20000 h	ISO 2578		°C	-	-
ELECTRIC PROPERTIES				d.a.m.*	cond.*
Volume Resistivity	IEC 62631-3-1		Ohm*cm	-	-
Surface Resistivity	IEC 63631-3-2		Ohm	-	-
Comparative Tracking Index (CTI)	IEC 60112	Solution A	V	600	-
FIRE BEHAVIOUR				d.a.m.*	cond.*
Flammability	UL 94	-	Class	-	-
Glow-wire Flammability	IEC 60695-2-12	-	°C	-	-
Burning Speed	FMVSS 302	2 mm	mm/min	<100	-



10005465 AQUAMID 66G15 NERO

Emission date 23/08/2024

Ed./Rev. 2.0

AQUAMID 66G15 NERO is a black color PA66 grade, filled with 15% glass fiber content and suitable for injection moulding applications.

HINTS

- It is recommended to dry the material before moulding at 80-90°C for 4-6 h; the suggested maximum moisture content is 0,15%.
- *d.a.m. specimens are tested dry as moulded, stored at room temperature and 50% RH. Conditioned specimens are tested according to internal method (24h @70°C in DI water + 30min @23°C in DI water).
- Injection moulding parameters have to be considered as a starting guideline and those shall be refined in the intended application, depending on available injection equipment.
- Technical parameters reported are typical of the product under aforementioned testing conditions but may vary according to particular processing conditions applied in the final product manufacturing.

(This document does not require signature as it is produced electronically)

AQUAFIL S.p.A. - Via Linfano, 9 - 38062 Arco (TN) - ITALIA

ISO 9001 e ISO 14001 Certified Quality System

GENERAL DISCLAIMER

The information provided in this document correspond to our technical knowledge at the date of its publication. This information may be subject to revision at our discretion. Aquafil cannot anticipate all conditions under which this information and/or products of other manufactures in combination with our products may be used. Aquafil accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Aquafil sells the product without warranties. Buyers and users assume all responsibilities and liability for loss or damage arising from handling and use of our product, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.